

Technical Data Sheet

GENERAL INFORMATION

INVINO-3250/3450 is defoamer based on mineral oil along with silicone.

TECHNICAL DATA SHEET

| | |
|--|-----------------------|
| Appearance | Light yellow emulsion |
| Density(g/cm³, 25°C) | 0.95 |
| Viscosity (25degree) | 800-5000 |
| Dispersity | Soluble in Water |
| Solid Content (%) | 60.0 |

APPLICATIONS

- Water-based adhesives
- Latex paints

KEY PROPERTIES

- High efficiency in wide latex and emulsion coating systems
- Water-soluble, dispersible, fast defoaming speed and long anti-foaming time
- Economical use can reduce the cost of formula
- Low added amount and easy to operate

LEVELS OF USE

- 0.2-0.6% based on total formulation with
- sufficient mixing
- Add INVINO-3250/3450 for two times, one time is during the grinding of the pigment, and the other during formulating the coating.

HANDLING AND STORAGE

- Avoid any eye and skin contact.
- Keep away from source of ignition and heat.
- Keep container tightly closed in a dry and well-ventilated place.
- Stored between 0°C-40°C.
- For further information please check to MSDS.

Our technical suggestions are based on data from many experiments and cannot represent a warranty of any kind as to their performance in other formulations. Customers must always verify our product's performance in their own systems. This technical data sheet replaces all previous issues.

Nanjing Invelychem Co., Ltd

Factory Address

No. 55. XINHAI Avenue, XUYI District, HUAIAN, China.

Tel: +86 25 58717026



Technical Data Sheet

PACKAGE

- Net Weight: 25kgs,200kgs/Plastic Drum.

SHELF LIFE

- Shelf life of 12 months from date of manufacture.

QUALITY ASSURANCE

We guarantee that all operations are conducted according to the stipulated standards. If you have any questions when you use. Please don't hesitate to contact us!

Invino

Our technical suggestions are based on data from many experiments and cannot represent a warranty of any kind as to their performance in other formulations. Customers must always verify our product's performance in their own systems. This technical data sheet replaces all previous issues.

Nanjing Invelychem Co., Ltd

Factory Address

No. 55. XINHAI Avenue, XUYI District, HUAIAN, China.

Tel: +86 25 58717026

