

## Technical Data Sheet

### GENERAL INFORMATION

INVINO-5060 is a non-silicone defoamer formulated with fatty alcohol. It exhibits excellent dispersibility, rapid air release, and strong dynamic defoaming and foam suppression capabilities. This product is specifically designed for effective foam control in the white water system of the papermaking process.

### TECHNICAL DATA SHEET

<b>Appearance</b>	Viscous White(Milk-like)
<b>Ionic Type of Emulsion</b>	Non anion
<b>PH</b>	6.0-8.0
<b>Viscosity (cps)</b>	100-1000
<b>Active Solid (%)</b>	30.0±1.0
<b>Density (g/cm<sup>3</sup>, 25°C)</b>	0.92-1.0

### APPLICATIONS

Wet end of papermaking (suitable for 50-60°C in white water)

### LEVELS OF USE

- INVINO-5060 can be used either as a concentrate or diluted according to process requirements.
- The optimal introduction point should be determined based on your specific production process and equipment layout to ensure maximum contact and efficacy.
- In general it is advisable to use it at 150-300g per one ton finished paper.

### HANDING AND STORAGE

- Avoid any eye and skin contact.
- Keep away from source of ignition and heat.
- Keep container tightly closed in a dry and well-ventilated place.
- Stored between 0°C-40°C.
- For further information please check to MSDS.

### PACKAGE

- Net Weight: 200kgs/Plastic Drum,IBC

### SHELF LIFE

Our technical suggestions are based on data from many experiments and cannot represent a warranty of any kind as to their performance in other formulations. Customers must always verify our product's performance in their own systems. This technical data sheet replaces all previous issues.

Nanjing Invelychem Co., Ltd

Factory Address

No. 55. XINHAI Avenue, XUYI District, HUAIAN, China.

Tel: +86 25 58717026



**INVINO-5060**



## Technical Data Sheet

- INVINO-5060 has a shelf life of 12 months from date of manufacture.

## QUALITY ASSURANCE

---

We guarantee that all operations are conducted according to the stipulated standards. If you have any questions when you use. Please don't hesitate to contact us!

invino

Our technical suggestions are based on data from many experiments and cannot represent a warranty of any kind as to their performance in other formulations. Customers must always verify our product's performance in their own systems. This technical data sheet replaces all previous issues.

**Nanjing Invelychem Co., Ltd**  
Factory Address  
No. 55. XINHAI Avenue, XUYI District, HUAIAN, China.  
Tel: +86 25 58717026

